

ألواح زينكوركوري

KOREAN ZINCOR SHEET

صفحة الزنكوركوري عبارة عن صفحة فولاذية تستخدم في تصنيع الحروف البارزة.

Zinc plate is a steel plate used in the manufacture of 3D letters.

المقاسات المتوفرة
AVAILABLE SIZE

THICKNESE (0.5 / 0.6 / 0.7 / 0.8 / 0.9 / 1.0)mm

SHEET SIZE 122x244 cm

Dimension (MM)			WEIGHT	Heat No	Quality	Hard ness [HRB]	Bending Test	Erichsen Test [B(mm)]	Tensile Test			Zn Coating		Surface Treatment		Chemical Composition(%)				
TH	W	L							YP [N/mm ²]	TS [N/mm ²]	EL [%]	TOP [g/m ²]	BOT [g/m ²]			C	SI	Mn	P	S
0.5	1219	2438.0	11.78 KGS	13349354501	JS-SECC	0	OK	OK	234	352	40	20	20	P	XX	0.038	0	0.2	0.014	0.007
0.56	1219	2438.0	13.19 KGS	AP27240	JS-SECC	0	OK	OK	235	352	43	20	20	P	XX	0.0193	0.003	0.182	0.0099	0.0075
0.68	1219	2438.0	15.98 KGS	13540224502	JS-SECC	0	OK	OK	223	347	42	20	20	P	XX	0.043	0.01	0.2	0.12	0.008
0.8	1219	2438.0	18.78 KGS	H235159600000	JS-SECC	0	OK	OK	317	242	48	20	20	P	XX	0.015	0	0.22	0.007	0.007
0.86	1219	2438.0	20.06 KGS	CSRC417	JS-SECC	0	OK	OK	236	343	40	20	20	P	XX	0.0387	0.006	0.145	0.0098	0.0039
1	1219	2438.0	23.45 KGS	AQ52988	JS-SECC	0	OK	OK	199	330	46	20	20	P	XX	0.0187	0.003	0.171	0.0089	0.006

*ECO Test Report

(Unit : mg/Kg)

Items	Cd	Pb	Hg	Cr VI	PBBs	PBDEs
Result	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.

note) n.d. = Not detected

* Tensile Test : Direction Longitudinal, Gauge Length 50mm

* Surface Treatment (Non Chromated / CR-Free coating)

:M-Non Phosphated, PU-Phosphated, A-Anti Finger Paint, C-Cr Free Treatment

We Hereby Certify That The Product Described Herein Has Been Satisfactorily Tested In Accordance With The Specification